




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B29B 11/16, 11/14		A1	(11) International Publication Number: WO 98/32579
			(43) International Publication Date: 30 July 1998 (30.07.98)
(21) International Application Number: PCT/GB98/00203		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).	
(22) International Filing Date: 23 January 1998 (23.01.98)		<p>Published With international search report.</p>	
(30) Priority Data: 9701500.2 24 January 1997 (24.01.97) GB			
(71) Applicants (for all designated States except US): BPB PLC [GB/GB]; Langley Park House, Uxbridge Road, Slough SL3 6DU (GB). MOY ISOVER LIMITED [IE/IE]; Clonskeagh Road, Dublin 4 (IE).			
(72) Inventors; and (75) Inventors/Applicants (for US only): WALTERS, John [GB/GB]; 29 Roundhill Road, Castleford, West Yorkshire WF10 5AG (GB). FITZSIMONS, Jocelyn [IE/IE]; 24 Margret Street, Georges Quay, Cork (IE).			
(74) Agent: MARLOW, Nicholas, Simon; Reddie & Grose, 16 Theobalds Road, London WC1X 8PL (GB).			

(54) Title: NON-WOVEN INORGANIC FIBRE MAT



(57) Abstract

A non-woven mat (18) of inorganic fibre is disclosed having a substance which is lower at the edges (26') of the mat than in the remainder (28) of the mat. Apparatus for making such a mat comprises: a source of a slurry of inorganic fibre in a liquid; a forming wire disposed to move past the source, through which the liquid passes to deposit the inorganic fibre on the forming wire; a mask across a part of the width of the forming wire to hinder passage of the liquid through the forming wire over the said part, the effectiveness of the mask varying in the direction of movement of the forming wire past the slurry source. A method of making the mat comprises passing a forming wire past a slurry of inorganic fibres in a liquid while masking a part of the width of the forming wire as it passes through the slurry, the masking varying along the length of the forming wire as it passes through the slurry; and urging the slurry against the forming wire and causing the liquid to pass through the forming wire, whereby a non-woven mat of inorganic fibre is formed having an uneven substance (weight/unit area) in the cross direction.